TECHNICAL DATA SHEET



ALPATEC 97096 2 part textile coating

Key Features

- Crosslinks at temperatures as of 23 °C/77°F
- Simple processing due to the low viscosity
- Simple mixing of the components
- Very good mechanical properties •

Revision Date	29 Apr 2021
Revision No	1
Download Date	24 Apr 2024

Property	Test Method	Value
Uncured Product		
Color		Transparent
Cure Type		Addition
Mix Ratio By Weight		1:1
Pot Life mins at		10 min mins
23°C/73°F		
Viscosity Mixed	Brookfield	77500 cP
Cured Product		
Density	BS ISO 2781	1.08 g/cm3
Elongation at Break	ISO 37	350 %
Hardness Shore A	DIN 53 505	50
Tear Resistance (N/mm)	BS ISO 34-1	20 N/mm / 114 ppi
Tensile Strength	ISO 37	6 N/mm2 / 870 psi

Storage

Max Storage Temperature Shelf Life

30 °C / 86 °F

12 mths

CHT Germany GmbH: Postfach 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany

Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, Homepage: www.cht.com / www.cht.silicones.com

The content set out in the technical data sheet does not contain information upon which you should rely. It is provided for general information purposes only and does not constitute a product

specification. You must obtain professional or specialist advice before taking any action based on the information provided in the technical data sheet. CHT make reasonable efforts to ensure that information set out in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or guarantees (whether express or implied) that information set out in the technical data sheet is complete, accurate, or up-to-date or that the product will be suitable for your requirements. You should carry out your own testing to determine the applicability of such information and whether the product will be suitable. CHT reserve the right to modify the technical data sheet at any time. The CHT technical service department is available to offer further information and advice and should it be needed to look at modifying current products or custom formulate a new one to meet your specific requirements. Please contact the technical service department.