

## KÖRAFORM 97036 2 part casting compound

### Description

Condensation crosslinking silicone casting compound for pad printing, shore A 12

### Key Features

- 100:3 mix ratio
- Low viscosity
- Suited printing pad manufacture
- Shore A 12

### Application

PAD printing

### Use and Cure Information

Prior to processing thoroughly stir up KÖRAFORM 97036 A to distribute homogeneously possibly deposited fillers. To the KÖRAFORM 97036 A the component KÖRAFORM B 128 K is added at a mixing ratio of 100 : 3 according to weight and then mixed with a spatula or stirrer until the compound is homogeneous.

With this mixing the potlife of 60 min starts where KÖRAFORM 97036 A must be processed (casting or brushing). Demoulding can be effected after 24 hours. For an absolutely bubble-free vulcanizate the mixed silicone gel must be degassed using vacuum prior to the casting process (5 min at the most at 10 – 20 mbar). The viscosity can be increased up to strength by adding up to 1 weight per cent KÖRAFORM TM C to the catalyzed compound. When casting critical grounds, e.g. glass, check the release behaviour with your own trials. A silicone-free release agent may have to be applied.

### Property

#### Uncured Product

Color A		<b>white</b>
Cure Type		<b>Condensation</b>
De-mould Time / Full Cure at 23°C/73°F		<b>24 hrs</b>
Density B	DIN 53 479	<b>0.99</b>
Mix Ratio By Weight		<b>100:3</b>
Pot Life mins at 23°C/73°F		<b>60 mins</b>
Viscosity A	Brookfield HBTD	<b>12000 cP</b>
Viscosity B	Brookfield HBTD	<b>14 cP</b>

#### Cured Product

**Standard climate DIN 50 014 - 23/50-2. Vulcanizate tested after 7 days at room temperature**

Color		<b>White</b>
Hardness Shore A	DIN 53 505	<b>12</b>
Linear Shrinkage (%)		<b>0.5 %</b>

#### Storage

Max Storage Temperature		<b>30 °C / 86 °F</b>
Min Storage Temperature		<b>5 °C / 41 °F</b>
Shelf Life		<b>6 mths</b>

### Solvents and Cleaning Agents

For removing fresh mass KÖRASOLV GL must be applied. Residues in the stirring or casting vessel can be easily removed by letting them cure in order to scrape them off afterwards.

### Storage

KÖRAFORM 97036 A can be optimally processed for at least six months if being stored at 5 °C – 30 °C in tightly closed original containers. KÖRAFORM B 128 K can be optimally processed for at least six months if being stored at 5 °C – 30 °C in tightly closed original containers.

### Health & Safety

#### Safety

Please observe our safety data sheets and the safety remarks on our container labels when handling our products. The dangerous goods regulations and the accident prevention regulations of the professional associations must be particularly observed. Keep the safety data sheet of the applied product at hand since it provides you with useful instructions for the safe use and disposal of the product as well as for actions to be taken in case of accidents.

Revision Date	27 Mar 2024
Revision No	3
Download Date	26 Apr 2024

The content set out in the technical data sheet does not contain information upon which you should rely. It is provided for general information purposes only and does not constitute a product specification. You must obtain professional or specialist advice before taking any action based on the information provided in the technical data sheet. CHT make reasonable efforts to ensure that information set out in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or guarantees (whether express or implied) that information set out in the technical data sheet is complete, accurate, or up-to-date or that the product will be suitable for your requirements. You should carry out your own testing to determine the applicability of such information and whether the product will be suitable. CHT reserve the right to modify the technical data sheet at any time. The CHT technical service department is available to offer further information and advice and should it be needed to look at modifying current products or custom formulate a new one to meet your specific requirements. Please contact the technical service department.

**CHT Germany GmbH:** Postfach 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany  
Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, Homepage: www.cht.com / www.cht-silicones.com