

## EM1539 Silicone Emulsion paintable

### Introduction

This is a water dilutable silicone emulsion, employed as a releasing agent for rubber and generally plastic materials. In the art graphic industry, it is mainly used as an antistatic and slip agent, it confers resistance to scratching during paper folding processes and protection to mechanical components.

### Key Features

- Compatible with paints
- Excellent release agent
- High temperature resistance
- Good dilution stability

### Use and Cure Information

#### Applications

This silicone emulsion has been formulated specially as a release agent and lubricant in a wide range of applications and processes such as:

- mould release agent
- release agent for bandaging of rubber tubes in vulcanisation process
- textile lubricant for yarn and thread as well as hosiery manufacture
- lubricant and antistatic in rotogravure off-set printing
- release agent for plastic tubes used to form bags and sacks
- gloss, slip and wettability in detergent and cleaner formulations

#### How to Use

This emulsion can be used either as supplied or diluted with water to the desired concentration, depending on the characteristics of the release and lubricant properties desired.

Dilutions of emulsion are stable, if the diluted emulsion is separated it is recommended to gently stir the emulsion to homogenize the system.

The concentration required for good release and lubricant properties depends on the process where it is employed. If there is no previous experience of a foam problem, it is generally suggested to start with a dilution of 1 part of Emulsion to 10 parts cold water and then to adjust the amount upwards or downwards to determine the most cost effective concentration.

In the graphic industry dilution required is usually 1:20 but this can vary depending on the kind of paper used.

#### Health and Safety:

Safety Data Sheets available on request.

#### Packaging:

CHT Emulsions are available in a variety of packaging and sizes including drums and IBC's. Please contact our sales department for more information.

Revision Date : 02/11/2017

Download Date : 27/02/2020

Property	Test Method	Value
% Silicone		35 %
% Solids		39 %
Appearance		Milky Liquid
Colour		White
FDA	CFR (21) 177.2600	No
Ionicity		Non-Ionic
Pharma Grade		No
Reactivity type		None
SG	BS ISO 2781	0.98
Silicone Yes/No		Yes
pH		6.5-8.5
<b>Storage</b>		
Max storage temperature °C		30 °C
Min storage temperature °C		5 °C
Shelf life		6 mths

The information and recommendations in this publication are to the best of our knowledge reliable. However, nothing herein is to be construed as warranty or representation. Users should make their own test to determine the applicability of such information or the suitability of any products for their own particular purposes. Statements concerning the user of the products described herein are not to be construed as recommending the infringement of any patent and no liability for infringement arising out of any such use is to be assumed. All values are typical and should not be accepted as a specification