

ALPATEC 30191 2 part textile coating

Key Features

- Sticky surface
- Good stability to chemicals
- High transparency
- Corresponds with Ökotex 100

Revision Date 29 Apr 2021
Revision No 1
Download Date 25 Apr 2024

Property

Uncured Product

Color	Transparent
Cure Profile	120 - 140 °C, 3 - 1 min.
Cure Type	Addition
Mix Ratio By Weight	1:1
Pot Life mins at 23°C/73°F	1 hr mins
Viscosity Mixed	Brookfield 72000 cP

Cured Product

Density	BS ISO 2781	1.1 g/cm ³
Elongation at Break	ISO 37	510 %
Hardness Shore A	DIN 53 505	22
Tear Resistance (N/mm)	BS ISO 34-1	14 N/mm / 80 ppi
Tensile Strength	ISO 37	5.3 N/mm ² / 769 psi

Storage

Max Storage Temperature	30 °C / 86 °F
Min Storage Temperature	5 °C / 41 °F
Shelf Life	6 mths

The content set out in the technical data sheet does not contain information upon which you should rely. It is provided for general information purposes only and does not constitute a product specification. You must obtain professional or specialist advice before taking any action based on the information provided in the technical data sheet. CHT make reasonable efforts to ensure that information set out in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or guarantees (whether express or implied) that information set out in the technical data sheet is complete, accurate, or up-to-date or that the product will be suitable for your requirements. You should carry out your own testing to determine the applicability of such information and whether the product will be suitable. CHT reserve the right to modify the technical data sheet at any time. The CHT technical service department is available to offer further information and advice and should it be needed to look at modifying current products or custom formulate a new one to meet your specific requirements. Please contact the technical service department.

CHT Germany GmbH: Postfach 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany
Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, Homepage: www.cht.com / www.cht-silicones.com