TECHNICAL DATA SHEET



EM 1463 Food grade 350 cSt polydimethylsiloxane emulsion

Description

Description	Property	Test	Value
This product is a food grade emulsion of a polydimethylsiloxane fluid.	Product	Method	
 Key Features Best in class dilution and formulation stability Has shown industry-best dilution stability at 1% actives Proven in food grade applications 	% Silicone Appearance Base Fluid Viscosity (cst) Density	BS ISO 2781	35 % White Emulsion 350 0.97 g/cm3
 Key Applications Mold Release Chain lubricant Food contact release agent Incidental food contact lubricant 	Viscosity (cst) pH Addition Rates		20 5
Application	Dosage - 1		1 part product to 30 parts water/aqueous media
EM 1463 is a high performing, ultrafine particle size emulsion of 350 centistoke polydimethylsiloxane fluid that is 35% active and has been formulated for direct food contact application. EM 1463 Is designed to be used as a denesting, antistatic release agent as well as conveyer chain lubricant in direct food contact	Storage Max Storage Temperature Min Storage Temperature		40 °C / 104 °F 4 °C / 39 °F
applications. Use and Cure Information	Packaging		460 lb. Drums or 2200 lb. Totes
This product can be diluted in water or an aqueous media before	Shelf Life		12 mths

use. If unsure where to start the dilution, it is recommended to dilute one-part product to 30 parts water/aqueous media. This dilution is then applied to the food contact surface by spraying, wiping, brushing, or dipping.

Health & Safety

This product is not intended for pharmaceutical use. It is the responsibility of the user to ensure acceptable compatibility with intended food contact surfaces.

Revision Date	25 Jan 2023
Revision No	8
Download Date	09 May 2024

The content set out in the technical data sheet does not contain information upon which you should rely. It is provided for general information purposes only and does not constitute a product specification. You must obtain professional or specialist advice before taking any action based on the information provided in the technical data sheet.

CHT Germany GmbH: Postfach 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany

Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, Homepage: www.cht.com / www.cht.silicones.com

CHT make reasonable efforts to ensure that information acted ut in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or guarantees (whether express or implied) that information set out in the technical data sheet is complete, accurate, or up-to-date or that the product will be suitable for your requirements. You should carry out your own testing to determine the applicability of such information and whether the product will be suitable. CHT reserve the right to modify the technical data sheet at any time. The CHT technical service department is available to offer further information and advice and should it be needed to look at modifying current products or custom formulate a new one to meet your specific requirements. Please contact the technical service department.