TECHNICAL DATA SHEET



HANSA SFA 42102 End capped vinyl siloxanes

Description	Property	Test Method	Value
All products of the HANSA SFA 42 series are end-capped vinyl siloxanes with different molecular weights and viscosities. The reactivity of the vinyl-functional polymers can be employed in addition as well as peroxide-activated curing systems.	Product Color Molecular weight g/mol Non-Volatile Content (%) Shelf Life Ultralow cyclic content Vinyl content mmol/g		Transparent 24000 g/mol
Addition-curing chemistry based on platinum cure is the basis for formulating silicone elastomers. Our vinyl polymers can serve as basis of these formulations to achieve different levels of viscosity, hardness, and mechanical properties. Using the HANSA SFA 42 series, you can ensure that your elastomer products are highly reactive, transparent, and low in volatiles.			> 99
			12 mths Yes 0.12 mmol/g
Key Features	Viscosity	Brookfield	1000 cP
 Excellent reactivity Good stability to UV, chemicals and weathering High transparency 	Uncured Product Cure Type		Additon cure
 No shrinkage during crosslinking Key Applications 	Cured Product Density	BS ISO 2781	0.97 g/cm3
 Intermediate for addition curing formulations Use and Cure Information 	Solubility		-
The preferred catalyst for the Hydrosilylation reaction is platinum	Solubility - Water		insoluble

catalyst from the ALPA-KAT series. It is advised to determine the

ratio of hydride to vinyl functional siloxane and the desired reaction component beforehand. Especially when using filled system, a hydride excess is needed.

All materials of the HANSA SFA 4 series are stable at ambient temperature under the exclusion of water.

All components should be well mixed to ensure the material is uniform. For best results, we recommend degassing afterwards.

Great care must be taken when handling and mixing all addition cured silicone elastomer systems, ensuring that all the mixing tools are clean and constructed in materials which do not interfere with the curing mechanism. The cure of the rubber can be inhibited by the presence of compounds of nitrogen, sulphur, phosphorus and arsenic; organotin catalysts and PVC stabilizers; epoxy resin catalysts and even contact with materials containing certain of these substances e.g. moulding clays, sulphur vulcanised rubbers, condensation cure silicone rubbers, onion and garlic.

These substances may impair or even completely prevent the curing behavior of addition crosslinking silicones typically indicated by tacky surfaces. Therefore, it is important to check the compatibility in preliminary tests if unknown substrates are used.

Health & Safety

Please observe our safety data sheets and the safety remarks on our container labels when handling our products. The dangerous goods regulations and the accident prevention regulations of the professional associations must be particularly observed. Keep the EC safety data sheet of the applied product at hand since it provides you with useful instructions for the safe use and disposal of the product as well as for actions to be taken in case of accidents.

CHT Polymers are available in a variety packaging including bulk containers. Please contact our customer service department for more information.

Revision Date29 Apr 2021Revision No1Download Date08 May 2024

CHT Germany GmbH: Postfach 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany

Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, Homepage: www.cht.com / www.cht-silicones.com

The content set out in the technical data sheet does not contain information upon which you should rely. It is provided for general information purposes only and does not constitute a product specification. You must obtain professional or specialist advice before taking any action based on the information provided in the technical data sheet.

CHT make reasonable efforts to ensure that information set out in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or guarantees (whether express or implied) that information set out in the technical data sheet is complete, accurate, or up-to-date or that the product will be suitable for your requirements. You should carry out your own testing to determine the applicability of such information and whether the product will be suitable. CHT reserve the right to modify the technical data sheet at any time. The CHT technical service department is available to offer further information and advice and should it be needed to look at modifying current products or custom formulate a new one to meet your specific requirements. Please contact the technical service department.