

QMCat Clear FG Food Grade Condensation Cure Catalyst for QM100 series

Description	Property	Test Method	Value
<p>This is a room temperature, two-component condensation cure catalyst for QM 107, QM 113, QM 122, QM 128, QM 140 and QM Skin 30. The cured rubber has excellent mechanical properties and good shelf life stability.</p> <p>Key Features</p> <ul style="list-style-type: none"> CFR 177.2600 compliant when used with one of the bases listed above. Quick tack-free time Relatively fast demold time Minimal impact on cured physical properties <p>Key Applications</p> <ul style="list-style-type: none"> Molds for polyester and polyurethane resin castings Indirect food contact applications Molds where hand mixing is required Glove molding applications <p>Use and Cure Information</p> <p>CURE CHARACTERISTICS</p> <p>Compliance with CFR 177.200 is dependent on mixing QM Cat Clear FG at a 10:1 (base:catalyst) ratio by weight with the QM 107, QM 113, QM 122, QM 128, QM 140 or QM Skin 30</p> <p>. Any compositional deviation will result in the material being non-compliant, due to lack of extraction testing on that particular composition. This applies to off ratio mixing as well as the use of any additives.</p> <p>Suitability for any application is to be determined by the end user. This material has not been subjected to tests appropriate for medical device or pharmaceutical applications.</p> <p>CHT makes no representations or warranties, either expressed or implied, of machinability, fitness for a particular purpose or any other nature with respect to the product to which the above information refers.</p> <p>The curing process begins as soon as the catalyst is mixed with the base. The material will cure as described in the data above under normal temperature (25°C) and humidity conditions (50% RH). Because this system is sensitive to heat and humidity, a change in cure speed may be observed if one or both of these variables are altered. A large difference in temperature (+/- 5°C) or humidity (> 60% – 70%) may alter the cure profile of the material. In addition, if the product is to be used with aggressive resins such as high styrene polyester resins, it is recommended that the rubber be allowed to cure for 48 hours.</p> <p>MIXING</p> <p>CHT recommends that the catalyzed material be tested on a small area of the mold prior to use.</p> <p>The base of the QM 100 series of products should be thoroughly mixed with the catalyst of choice using a 10:1 ratio (base:catalyst) by weight. Shake the catalyst well before use. Material should be mixed in a clean, compatible metal or plastic container. The volume of the container should be 3 - 4 times the volume of the material to be mixed. This allows for expansion of the siloxane material during de-aeration. Mix thoroughly by hand or with mixing equipment while minimizing air entrapment until a homogeneous mixture is obtained. This will occur when the material takes on a uniform color with no visible striations. Machine mixing is recommended for best results.</p> <p>DE-AERATION</p> <p>Air trapped during mixing should be removed by vacuum at 29 inches of mercury. During the process, the material will expand, and intermittent evacuation may be required. Typically, after releasing the vacuum 2 - 3 times, the mass will collapse on itself at which time the vacuum should be left on for an additional 2 - 4 minutes.</p> <p>Health & Safety</p> <p>Safety</p> <p>Please observe our safety data sheets and the safety remarks on our container labels when handling our products. The dangerous goods regulations and the accident prevention regulations of the professional associations must be particularly observed. Keep the safety data sheet of the applied product at hand since it provides you with useful instructions for the safe use and disposal of the product as well as for actions to be taken in case of accidents.</p>	Uncured Product		
	Appearance		Liquid
	Color		Translucent
	Cure Type		Condensation
	De-mould Time / Full Cure at 23°C/73°F		12 to 16 hrs
	Mix Ratio By Weight		10 to 1
	Pot Life mins at 23°C/73°F		15 to 45 mins
	Specific Gravity		1.01
	Tack Free Time / Skin Formation at 23°C/73°F		4 to 6 hrs
	Viscosity	Brookfield	250 to 500 cP
	Storage		
	Max Storage Temperature		38 °C / 100 °F
	Shelf Life		12 mths

MIXING

CHT recommends that the catalyzed material be tested on a small area of the mold prior to use.

The base of the QM 100 series of products should be thoroughly mixed with the catalyst of choice using a 10:1 ratio (base:catalyst) by weight. Shake the catalyst well before use. Material should be mixed in a clean, compatible metal or plastic container. The volume of the container should be 3 - 4 times the volume of the material to be mixed. This allows for expansion of the siloxane material during de-aeration.

Mix thoroughly by hand or with mixing equipment while minimizing air entrapment until a homogeneous mixture is obtained. This will occur when the material takes on a uniform color with no visible striations. Machine mixing is recommended for best results.

DE-AERATION

Air trapped during mixing should be removed by vacuum at 29 inches of mercury. During the process, the material will expand, and intermittent evacuation may be required. Typically, after releasing the vacuum 2 - 3 times, the mass will collapse on itself at which time the vacuum should be left on for an additional 2 - 4 minutes.

Health & Safety

Safety

Please observe our safety data sheets and the safety remarks on our container labels when handling our products. The dangerous goods regulations and the accident prevention regulations of the professional associations must be particularly observed. Keep the safety data sheet of the applied product at hand since it provides you with useful instructions for the safe use and disposal of the product as well as for actions to be taken in case of accidents.

Revision Date 27 Oct 2021
Revision No 5
Download Date 09 May 2024

The content set out in the technical data sheet does not contain information upon which you should rely. It is provided for general information purposes only and does not constitute a product specification. You must obtain professional or specialist advice before taking any action based on the information provided in the technical data sheet. CHT make reasonable efforts to ensure that information set out in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or guarantees (whether express or implied) that information set out in the technical data sheet is complete, accurate, or up-to-date or that the product will be suitable for your requirements. You should carry out your own testing to determine the applicability of such information and whether the product will be suitable. CHT reserve the right to modify the technical data sheet at any time. The CHT technical service department is available to offer further information and advice and should it be needed to look at modifying current products or custom formulate a new one to meet your specific requirements. Please contact the technical service department.

CHT Germany GmbH: Postfach 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany
Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, Homepage: www.cht.com / www.cht-silicones.com