

## SE2005 2 part encapsulation and potting silicone

### Description

This is a 2-component, silicone elastomer system specially designed for electronic potting and encapsulation applications. It offers good protection against chemicals, environmental contamination, mechanical shock, vibration and impact damage. It can be employed in areas where low flammability is a prerequisite. The cured elastomer can be repaired. The component parts have relatively low viscosities and are readily mixed either by hand or machine

### Key Features

- Low viscosity
- Deep section cure
- Excellent dielectric properties
- Protects against shock and vibration

### Application

Protects against shock/vibration.

### Use and Cure Information

The product is supplied as two components 'A' and 'B'. These components should be mixed together in the ratio by weight shown opposite. Mixing can be done by hand or by automated dispensing machine using a static mixer nozzle. A nozzle of at least 9 GXF type elements is recommended for uniform mixing of both components.

The dispensing machine mix ratios should be adjusted if mixing by volume and not weight. IMPORTANT the mixed components will cure in the nozzle so to preserve nozzles a continuous process is required or a change of nozzle after the task is completed. Complete mixing of each component is achieved within the first 50-60% of the nozzle.

### Mixing

Both the 'A' and 'B' parts should be well stirred to ensure the material is uniform and any settlement of the fillers have been remixed.

Place the required amount of 'A' and 'B' parts by weight at the mix ratio shown opposite, in a clean plastic or metal container of approximately 3 times their volume, and mix until the colour of the mixture is uniform. For best results, we recommend degassing. Degas by intermittent evacuation, the larger volume of the mixing vessel helps prevent overflow during this operation. In case of automatic dispensing with static mixing head, the two components should be degassed before processing. Recommended vacuum conditions are 30-50 mbar intermittently over 5-10 minutes. Cast the mixture either by gravity or pressure injection.

It is important to check the compatibility in preliminary tests if unknown substrates are used.

### Health & Safety

#### Health and Safety

Safety Data Sheets available on request.

### Packaging

CHT Encapsulants are available in a variety packaging including bulk containers. Please contact our sales department for more information.

Revision Date      29 Apr 2021  
Revision No        1  
Download Date     03 May 2024

### Property

#### Uncured Product

Property	Test Method	Value
Cure Type		Condensation
De-mould Time / Full Cure at 23°C/73°F		24 hrs
Density A	BS ISO 2781	1.21
Density B	BS ISO 2781	1.14
Mix Ratio By Weight		100:1
Pot Life mins at 23°C/73°F		1 hr mins
Rheology		Liquid
Viscosity A	Brookfield	9000 cP
Viscosity B	Brookfield	300 cP
Viscosity Mixed	Brookfield	9000 cP

#### Cured Product

##### 7 days at 23+/-2°C and 50+/-5% humidity

CTE Volumetric ppm/°C		762 ppm/°C
Color		White
Density	BS ISO 2781	1.20 g/cm3
Elongation at Break	ISO 37	180 %
Hardness Shore A	ASTM D 2240-95	40
Linear Shrinkage (%)		0.5 %
Max Working Temp		220 °C / 428 °F
Min Working Temp		-50 °C / -58 °F
Tear Resistance (N/mm)	BS ISO 34-1	2 N/mm / 11 ppi
Tensile Strength	ISO 37	1.08 N/mm2 / 157 psi
Thermal Conductivity		0.24 W/mK

#### Electrical Properties

Dielectric Constant	ASTM D-150	3.4
Dielectric Strength kV/mm	ASTM D-149	>18 kV/mm / 0 V/mil
Volume Resistivity (Ohms cm)	ASTM D-257	3E+14 ohms cm

#### Storage

Max Storage Temperature	40 °C / 104 °F
Shelf Life	9 mths

The content set out in the technical data sheet does not contain information upon which you should rely. It is provided for general information purposes only and does not constitute a product specification. You must obtain professional or specialist advice before taking any action based on the information provided in the technical data sheet. CHT make reasonable efforts to ensure that information set out in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or guarantees (whether express or implied) that information set out in the technical data sheet is complete, accurate, or up-to-date or that the product will be suitable for your requirements. You should carry out your own testing to determine the applicability of such information and whether the product will be suitable. CHT reserve the right to modify the technical data sheet at any time. The CHT technical service department is available to offer further information and advice and should it be needed to look at modifying current products or custom formulate a new one to meet your specific requirements. Please contact the technical service department.

CHT Germany GmbH: Postfach 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany  
Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, Homepage: www.cht.com / www.cht-silicones.com