

## Silcoset Primer Primer

### Description

Silcoset® Primer is a complex solvent solution of a silicone resin based primer specially developed for use with CHT 1 and 2K condensation / moisture curing RTV silicone sealants and elastomers. It is recommended for improved adhesion to most metals, glass, plastics and composites. Silcoset® Primer contains a pink dye that aids application of uniform thin coatings. For all new applications, it is recommended that customers carry out small-scale tests to determine the suitability of the primer and the strength of bond produced.

® = registered trademark

### Key Features

- Aerospace approved
- For use with Silcoset 1 and 2 component elastomers
- Good resistance to water immersion
- Pink fluorescent dye for inspection aid

### Key Applications

- Rolls Royce MSRR 9103
- NATO Stock code: 8030-99-224-1407

### Application

For use with Silcoset 1 and 2 part condensation cure elastomers, not suitable for polycarbonate and acrylic

### Use and Cure Information

This primer contains solvents which are classified as hazardous under current regulations. Users should read the Safety Data Sheets for this product carefully before use. Surfaces to be bonded should be dry and free from grease, oil, dust and release agents. Non-porous substrates should be solvent degreased prior to application. The primer should be applied with a lint-free cloth or paintbrush and allowed to dry thoroughly at room temperature for a minimum time equal to the tack free time given in this document, before applying the sealant. Drying should be carried out in a well ventilated area. Do not leave longer than 2 hours. The drying/curing time is dependent on the ambient temperature and humidity. Heat should not be applied to accelerate the drying cycle. Over-application of the primer will result in poor adhesion. As a guide, one litre of Primer should be sufficient for approximately 15 m<sup>2</sup>. It is very important to check the compatibility in preliminary tests if unknown substrates are used.

### Health & Safety

#### Safety

Please observe the safety data sheets and the safety statements on the container labels when handling our products. The dangerous goods regulations and the accident prevention regulations of the professional associations must be particularly observed. Keep the safety data sheet of the applied product at hand since it provides useful instructions for the safe use and disposal of the product as well as for actions to be taken in case of accidents.

Revision Date      29 Apr 2021  
Revision No        1  
Download Date     09 May 2024

Property	Test Method	Value
<b>Product</b>		
Solids Content (%)		15 %
<b>Uncured Product</b>		
<b>23 +/-2°C and 50 +/-5% humidity</b>		
Color		Pink
Cure Profile		23+/-2°C and 50+/-5% humidity
Density	BS ISO 2781	0.86 g/cm3
Flash Point °C	BS 2000-34	-12 °C
Odour		Solvent
Rheology		Liquid
Tack Free Time / Skin Formation at 23°C/73°F		15 min
Viscosity Mixed	Brookfield	4 cP
<b>Storage</b>		
Max Storage Temperature		25 °C / 77 °F
Min Storage Temperature		5 °C / 41 °F
Shelf Life		12 mths

The content set out in the technical data sheet does not contain information upon which you should rely. It is provided for general information purposes only and does not constitute a product specification. You must obtain professional or specialist advice before taking any action based on the information provided in the technical data sheet.

CHT make reasonable efforts to ensure that information set out in the technical data sheet is complete, accurate, and up-to-date. CHT do not, however, make any representations, warranties or guarantees (whether express or implied) that information set out in the technical data sheet is complete, accurate, or up-to-date or that the product will be suitable for your requirements. You should carry out your own testing to determine the applicability of such information and whether the product will be suitable. CHT reserve the right to modify the technical data sheet at any time. The CHT technical service department is available to offer further information and advice and should it be needed to look at modifying current products or custom formulate a new one to meet your specific requirements. Please contact the technical service department.

**CHT Germany GmbH:** Postfach 12 80, 72002 Tübingen, Bismarckstraße 102, 72072 Tübingen, Germany  
Telephone: 07071/154-0, Fax: 07071/154-290, Email: info@cht.com, Homepage: www.cht.com / www.cht-silicones.com